

TECHNISCHE WERTE
 TECHNICAL SPECIFICATIONS
 ТЕХНИЧЕСКИЕ ДАННЫЕ
 SCHEDA TECNICA


KERAPLATTE® TERRA

DIN EN 14411


Bezeichnung/Description/ Обозначение артикула/Descrizione	Format/Size/Обозначение артикула/ Formato	Artikelnummer/Order number/ номер артикула/Articolo	Farbe/Colour/Liçer/Colore
Extrudierte Bodenfliese	12,5 x 25 cm	1100	307 weizengelb, 316 patrizierrot ofenbunt, 215 patrizierrot
Extrudierte Bodenfliese	25 x 25 cm	1610	307 weizengelb, 316 patrizierrot ofenbunt, 215 patrizierrot
Extrudierte Bodenfliese	12,5 x 30 cm	9310	215 patrizierrot
Extrudierte Bodenfliese	25 x 30 cm	9320	215 patrizierrot

 Wasseraufnahme (Mittelwert) Water absorption (Average value) Водопоглощение (среднее значение) Assorbente acqua (Valore medio) (EN ISO 10545-3):	≤ 3 % 307 weizengelb: 3% ≤ 6 %
---	---------------------------------------

 Biegefestigkeit (Mittelwert) Bending strength (Average value) Прочность на изгиб (среднее значение) Resistenza alla flessione (Valore medio) (EN ISO 10545-4):	≥ 28 N/mm ²
--	------------------------

 Ritzhärte nach Mohs (kleinster Einzelwert) Scratch hardness of surface (Mohs scale) (minimum individual value) Твердость по шкале Мооса (меньшее значение) Durezza selerometrica sec. Mohs (valore singolo minore) (EN 15771):	6-7
---	-----

 Verschleißwiderstand der Oberfläche für glasierte Platten Resistance of surface abrasion for glazed tiles Износостойкость поверхности глазурованных плиток Resistenza all'usura superficiale per piastrelle smaltate (EN ISO 10545-7):	≤ 275 mm ³
---	-----------------------

 Thermischer LAK von Raumtemperatur (20° C) bis 100° C Coefficient of thermal expansion from room temperatur (20° C) to 100° C Кэффициент термического расширения от комнатной температуры (20° C) до 100° C Coefficiente di dilatazione in lunghezza a temperatura ambiente (20° C) fino a 100°C (EN ISO 10545-8):	< 80x10 ⁻⁷ K ⁻¹
---	---------------------------------------

 Temperaturwechselbeständigkeit Thermal shock resistance Термостойкость Resistenza agli sbalzi di temperatura (EN ISO 10545-9):	erfüllt/is fulfilled/Выполнено/conforme
---	---

 Frostbeständigkeit frost resistance Морозоустойчивость Resistenza al gelo (EN ISO 10545-12):	erfüllt/is fulfilled/Выполнено/conforme
---	---



Chemische Beständigkeit – außer gegen Flußsäure und ihre Verbindungen – für Fliesen und Platten

Chemical resistance – except to hydrofluoric acid and its compounds – of tiles
Химическая устойчивость — кроме плавиковой кислоты (фтористоводородной) и ее соединений — для глазурованной и неглазурованной плитки
Resistenza agli agenti chimici – ad eccezione dell'acido fluoridrico e dei suoi composti – per piastrelle
(EN ISO 10545-13):

erfüllt/is fulfilled/Выполнено/conforme



Bewertungsgruppe für rutschhemmende Bodenbeläge im nassbelasteten Barfußbereich

Classification groups for antislip floor claddings in barefoot areas
Коэффициент сопротивления скольжению для влажных напольных покрытий при ходьбе босиком
Gruppi di valutazione per rivestimenti antisdrucciolevoli per pavimenti in zona dove si cammina a piedi nudi sul bagnato
(DIN EN 16165 Anhang A):

Bodenfliesen/floor tiles/Напольная плитка/
pavimento
Gruppe/Group/Группа/Gruppo: B



Bewertungsgruppe für gewerbliche Bodenplatten mit erhöhter Rutschgefahr (Begehungsverfahren)

Classification groups for industrial floor claddings with an increased risk of slipping (safety procedure)
Коэффициент сопротивления для промышленных помещений с повышенным риском скольжения
Gruppi di valutazione per rivestimenti di pavimenti industriali con elevato pericolo di sdrucciolevolita' (procedimento di controllo)
(DIN EN 16165 Anhang B):

Gruppe/Group/Группа/Gruppo: R 11

Ströher GmbH

Ströherstraße 2-10

35683 Dillenburg

Telefon: +49 2771 391-0

Telefax: +49 2771 391-340

E-Mail: info@stroeher.de

www.stroeher.de

Ströher GmbH

i. V. Jochen Keil

Laborleiter